



## Test Report

No: TX40969 /2009 /SH

Date: Apr. 17, 2009

Page: 1 OF 2

Golden State Industrial Co., Ltd.  
No. 18, Lane 350, Sec. 3, Tamchin Road, Tamshui,  
Taipei, Taiwan, R.O.C.

The following sample was submitted and identified by the client as:

Sample Description : One sample of woven fabric modified polyester taffeta,  
two-side coated in white

Fiber Content : Polyester

Style No. : NP216A6


Sample Receiving Date : Apr. 13, 2009

Test Performance Period : Apr. 13 to Apr. 17, 2009

Test Performed : Selected test(s) as requested by applicant.

Test Results : For further details, please refer to the following page(s).

Signed for and on behalf of  
SGS Taiwan Ltd.

  
Lin Mei Yin, Maggie  
Technician

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明，此報告結果僅對測試之樣品負責。本報告未經本公司書面許可，不可部份複製。

This Test Report is issued by the Company under its General Conditions of Service printed overleaf or available on request and accessible at [http://www.sgs.com/terms\\_and\\_conditions.htm](http://www.sgs.com/terms_and_conditions.htm). Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this Test Report is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

SGS Taiwan Ltd.  
台灣檢驗科技股份有限公司

No.31 Wu Chyuan Road, Wuku Industrial Zone, Taipei County, Taiwan. /台北縣五股工業區五權路31號  
t (886-2) 2299-3939

f (886-2) 2299-3227

www.tw.sgs.com

TWA 0174151



**Test Report**

No: TX40969 /2009 /SH

Date: Apr. 17, 2009

Page: 2 OF 2

**Test Requested:**

For compliance with Federal Motor Vehicles Safety Standard No.302  
Flammability of interior materials.

**Test Results:**

Pass

Sample

	Lengthwise			Widthwise		Burn Rate (mm/min)
	Char Length (mm)	After Flame (sec.)	Burn Rate (mm/min)	Char Length (mm)	After Flame (sec.)	
1.	21	18	SE/NBR	-	-	D.N.I.
2.	-	-	D.N.I.	-	-	D.N.I.
3.	-	-	D.N.I.	-	-	D.N.I.

Note: SE/B = Self Extinguish with a burn rate in mm/minute Flame  
extinguishes itself before reaching the 38 mm point from  
the clamped end of the specimen.

SE/NBR = Self Extinguishing/No Burn Rate. The material stops burning  
before it has burned for 60 seconds from the start of timing and  
has not burned more than 51 mm from the point where  
timing was started.

D.N.I. = Does not ignite. The material does not support combustion during  
or following the 15 second ignition period.

**Test Requirements:**

The burn rate shall not exceed 102mm per minute.

**Conclusion:**

In our opinion, the submitted sample(s) complies with Federal Motor Vehicle Safety  
Standard No. 302 Flammability of interior materials (49 CFR 571.302 10-1-08 Edition).

The test was subcontracted to other SGS Laboratory.

\*\*\* End of Report \*\*\*

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. 除非另有說明，此報告結果僅對測試之樣品負責。本報告未經本公司書面許可，不可部份複製。

This Test Report is issued by the Company under its General Conditions of Service printed overleaf or available on request and accessible at [http://www.sgs.com/terms\\_and\\_conditions.htm](http://www.sgs.com/terms_and_conditions.htm). Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this Test Report is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.